



Transformer Oil Uninhibited

Efficient performance transformer oil

Product description

Transformer Oil Uninhibited is a highly refined, efficient performance uninhibited transformer oil, providing high dielectric strength and effective low temperature performance. It is formulated with a mineral base stock and provides good oxidation stability.

Transformer oil fulfils the requirements of an IEC 60296 Edition 5.0, Type B, TVBU Uninhibited Oil. It passes all of the following corrosion tests: ASTM D1275; IEC 62535 and DIN 51353.

Customer benefits

- High dielectric strength.
- Effective low temperature performance.
- Oxidation stability contributes to long service life.
- Passes the 2006 Oil/Copper interactions tests as described in ASTM D 1275B.
- Offers neutral behaviour with insulating materials.
- 100% recyclable.

Product highlights

- **High dielectric strength**
- **Effective low temperature performance**
- **Long service life**
- **100% recyclable**

Selected specification standards include:

IEC

BS

Applications

- Transformer Oil Uninhibited is used as an insulating oil in transformers, switchgear, inductors, condensers, transducers and similar equipment, also at low temperatures in outdoor use.
- It insulates current-carrying parts from each other and from ground, carries away heat, prevents glow discharges, extinguishes electric arcs in switchgear, and impregnates insulating materials.

Approvals, performance and suitable for use

Performance

Transformer Oil Uninhibited meets the requirements of:

- IEC 60296 Edition 5.0 Uninhibited Oil
- BS 148 IIA (1998)
- This oil tested non-corrosive with CIGRE A2.32 preferred method.

Typical test data

Test	Test methods	Results
Shelf Life: 12 months from date of filling indicated on the product label.		
Appearance	IEC 60296	Clear
Colour	ISO 2049	<0.5
Density at 20°C	ISO 3675	0.871 kg/dm ³
Flash Point, PM	ISO 2719	150°C
Pour Point	ISO 3016	- 45°C
Kinematic Viscosity at 40°C	ISO 3104	10 mm ² /s
Neutralization Value (Acidity)	IEC 62021	<0.01 mg KOH/g
Water Content	IEC 60814	<20 mg/kg or ppm
Breakdown Voltage		
- Before Treatment	IEC 60156	40-60 kV
- After Treatment	IEC 60296/60156	>70 kV

The typical test data set out above does not constitute a specification. It is indicative only and can be affected by allowable production tolerances. Chevron may modify this test data. Modified data will supersede all previous data, so please ensure you refer to the latest version of this Product Data Sheet (PDS).

Disclaimer: Data provided in this Product Data Sheet (PDS) is based on standard tests under laboratory conditions and is indicative only. This product should not be used for any purpose other than those expressly set out in this PDS. The user has sole responsibility for verifying that this product is suitable for the user's intended application. Neither Chevron nor its subsidiaries (i) make any warranty or representation as to the accuracy or completeness of this PDS; and/or (ii) accept liability for any loss or damage suffered as a result of the use of this product other than in accordance with the terms of this PDS.

Always confirm that the product selected is consistent with the original equipment manufacturer's recommendation for the equipment operating conditions and customer's maintenance practices.

When disposing of used product, take care to protect the environment and follow local legislation.

Safety Data Sheets (SDS's) are available for all Chevron products. If you require a SDS or any further information regarding a Chevron product, please contact your local sales office or see www.texacolubricants.com.

A **Chevron** company product