



CHEVRON OPEN GEAR LUBRICANT

250 NC

PRODUCT DESCRIPTION

Chevron Open Gear Lubricant is formulated to minimize wear and provide shock load protection during typical operations.

CUSTOMER BENEFITS

Chevron Open Gear Lubricant delivers value through:

- **Low environmental impact** — The carrier solvent contained in Chevron Open Gear Lubricant is a non-ozone depleting diluent. Chevron Open Gear Lubricants also pass the EPA's Toxicity Characteristic Leaching Procedure (TCLP) test.
- **Long equipment life** — High film strength provides excellent anti-wear protection to gear teeth under high, shock load conditions.
- **Ease of application** — Easily applied with brushes, swabs or through automatic lubrication systems.

FEATURES

Chevron Open Gear Lubricant is a black, viscous lubricant formulated with an asphaltic base and diluted with a non-chlorinated solvent for easy application by hand or through automatic lubrication systems.

It provides a high film strength coating on gear teeth to minimize wear.

Chevron Open Gear Lubricant is designed to provide tacky, tenacious lubricant films on open gears operating under severe shock load conditions.

Chevron Open Gear Lubricant contains a non-chlorinated diluent that eases the application of these lubricants onto the gears. The diluent then evaporates, leaving a tacky lubricant film on the gear teeth.

It can also be used to lubricate chains, sprockets, wire rope, and cables. When used as a cable coating, the diluent allows the lubricant to penetrate into the core, thus carrying the lubricant into the individual strands and minimizes wear as the cable is run through sheaves or onto a winch drum.

APPLICATIONS

Chevron Open Gear Lubricant is recommended for many types of open gears, wire ropes, and cables.

It can be applied by brush, by swab or by automatic lubrication systems.

It provides lubrication for mining equipment, including:

- girth and pinion gears on rod and ball mills;
- rack and pinion gears on shovel dipsticks;
- swing and pinion gears on top of the lower frame of shovels and draglines, which are sometimes served with an automatic lubrication system.

Product(s) manufactured in the USA.

Always confirm that the product selected is consistent with the original equipment manufacturer's recommendation for the equipment operating conditions and customer's maintenance practices.

A **Chevron** company product

1 December 2022
GL-65

© 2009-2022 Chevron U.S.A. Inc. All rights reserved.

Chevron and the Chevron Hallmark are trademarks owned by Chevron Intellectual Property LLC. All other trademarks are property of their respective owners.

TYPICAL TEST DATA

	250 NC
<i>Product Number</i>	255141
<i>SDS Number</i>	7088
Contains Diluent ^a	Yes
Thickener Type	Asphaltic
Timken OK Load, ASTM D2782, lb	40
Four-Ball Weld Point, ASTM D2783, kg Wear Scar Diameter, ASTM D2266, mm	315 0.60
Rust Test, ASTM D665, 24 h, Distilled Water	Pass
Viscosity, Kinematic cSt at 40°C (with diluent) cSt at 100°C (without diluent)	4125 800
Viscosity, Saybolt SUS at 100°F (with diluent) SUS at 210°F (without diluent)	19,110 3730
Low Temperature Pumpability Lincoln Ventmeter at 400 psi, °C(°F)	0(32)
Flash Point, °C(°F)	83(181)
Pour Point, °C(°F)	4(40)
Resultant Film ^b	Tacky
Texture	Smooth
Color	Black

a Diluent is nonchlorinated and combustible. It is also volatile, therefore it is important to keep containers tightly sealed to avoid loss.

b At normal ambient temperature 21°C to 38°C (70°F to 100°F).

Minor variations in product typical test data are to be expected in normal manufacturing.

Always confirm that the product selected is consistent with the original equipment manufacturer's recommendation for the equipment operating conditions and customer's maintenance practices.