

Rykon HD2 M5

Premium Performance Extreme Pressure Moly Grease



Product description

Rykon HD2 M5 features a boost of 5% moly product to meet the demands of OEMs of off-road applications. They feature great shock loading and provide anti-weld protection.

Customer benefits and product features

Customer benefits

Rykon HD2 M5 greases deliver value for the off-road construction and mining industries by offering:

- **Extreme pressure high-load carrying capacity**
Protection against shock loading, thus promoting long bearing life.
- **Excellent corrosion and wear protection**
Especially in wet conditions.
- **Excellent water resistance**
Good resistance to wash-out of bearings in submerged or direct spray situations.
- **Excellent high temperature stability**
Offers lasting bearing protection.
- **Outstanding low temperature pumpability**
Easy handling in the container and grease dispensing equipment.

Product features

Rykon HD2 M5 greases utilize an overbased calcium complex thickener system that produce multipurpose, high-performance products that protect against corrosion, wear, have high dropping points and good thermal stability. They are specially formulated for plain and anti-friction bearing applications operating under high stress/high load and wet conditions typically found in heavy duty off-road applications. This line of grease was specifically designed to lubricate and protect equipment that is subjected to demanding conditions.

Rykon HD2 M5

Premium Performance Extreme Pressure Moly Grease



Applications

Rykon HD2 M5 greases are designed for extreme duty in a wide variety of on-highway and light duty off-road vehicle and equipment applications.

Off-Road Construction

These greases display outstanding water washout and spray-off resistance properties in wet, off-road environments and offer excellent shock load extreme pressure (EP) protection. Unique additive technology of these products makes them tenacious at adhering to metal surfaces found in this industry while protecting these vital components from rust and corrosion.

Applications for the product include most types of heavy-duty earth moving machinery, including tractors (dozers), excavators, backhoes, shovels, high lifts, articulated loaders, haul trucks, tri-axle dumps and more. They are excellent for heavily loaded machine implement pins and bushings, and other applications operating in severe, high shock load environments where metal to metal contact wear often occurs. They also meet Caterpillar recommendations for greases containing 5% molybdenum disulfide.

Light Duty Off-Road Vehicles

Whether the application is in logging, agriculture or utilities, these greases will perform. Use them in tractors, cherry pickers or any of a number of light duty off road vehicles.

Approvals, performance and recommendations

Rykon HD2 M5 greases are approved for the NLGI Certification Mark GC-LB.



Rykon HD2 M5

Premium Performance Extreme Pressure Moly Grease



Typical test data

RYKON HD2 M5		
Product Code		540948
Operating temperature, °C (°F)		
Minimum ^a		-20(-4)
Maximum ^b		177(350)
ISO Viscosity Grade Base Oil Equivalent		460
Base Oil Viscosity, Kinematic		
cSt @ 40°C	ASTM D445	460
cSt @ 100°C	ASTM D445	31
Base Oil Viscosity Index	ASTM D2770	97
Thickener Type		Calcium Sulfonate Complex
Penetration, at 25°C Worked (60 stroke)	ASTM D217	280
Dropping Point, °C	ASTM D2265	308
Four Ball		
Weld Point, kg	ASTM D2596	800
Load Wear Index, kg	ASTM D2596	111
Four Ball Wear Scar, mm	ASTM D2266	0.43
Timken OK Load, lb	ASTM D2509	75
Copper Corrosion 3h at 100°C	ASTM D4048	1b
Bearing Rust	ASTM D1743	Pass
Salt Fog Test, hrs	ASTM B117	>1000
Water Washout, wt% loss at 80°C	ASTM D1264	2.5
Water Spray-off, wt% at 38°C	ASTM D4049	29
Flow Pressure at -20°C, mbar	DIN 51 805	1103
Oil Separation, wt%	ASTM D1742	0.0
Molybdenum Disulfide Content, %		5
Texture		Tacky
Color		Grey/Black

Rykon HD2 M5

Premium Performance Long Life Grease



Typical test data *cont...*

- a. Minimum operating temperature is the lowest temperature at which a grease, already in place, could be expected to provide lubrication. Most greases cannot be pumped at these minimum temperatures.
- b. Maximum operating temperature is the highest temperature at which the grease could be used with frequent (daily) relubrication.

Minor variations in product typical test data are to be expected in normal manufacturing.

This bulletin was prepared in good faith from the best information available at the time of issue. While the values and characteristics are considered representative, some variation, not affecting performance, can be expected. It is the responsibility of the user to ensure that the products are used in the applications for which they are intended. Produced by Chevron Global Lubricants: Asia Pacific.

ENVIRONMENT, HEALTH and SAFETY. Information is available on this product in the Material Safety Data Sheet (MSDS) and Customer Safety Guide. Customers are encouraged to review this information, follow precautions and comply with laws and regulations concerning product use and disposal. To obtain a MSDS for this product, visit the [Product Information Center](#).

This Product Data Sheet (PDS) was produced for the Asia Pacific region based on the best available information at the time of issue. The specific information included may not directly reflect the market or conditions, and may vary. For the most up-to-date, country-specific information, please contact your local customer service center.

[Visit Product Information Center >](#)

Rykon HD2 M5/Asia Pacific/CHV/PDSv1_04/2024



A Chevron company product

© 2024 Chevron Products Company. Asia Pacific.
All Rights Reserved.