



Marfak Na XD 00

Proven performance sodium soap grease

(Previously known as Marfak 00)

Product description

Marfak Na XD 00 is a proven performance fibrous sodium thickened grease designed to lubricate track rollers of crawler tractors, steering gears, and final drives of tractors, and industrial gearboxes, providing a tough durable film, good adhesion and cohesion.

Marfak Na XD 00 is based on a sodium thickener, designed to help provide inherent rust protection by emulsifying small amounts of water, with good sealing properties.

Customer benefits

- Good film strength contributes to effective wear protection.
- Offers resistance against rust and dirt ingress.
- Formulated to emulsify small amounts of water.
- Designed to help provide inherent rust protection.

Product highlights

- **Formulated for effective adhesion and good film strength.**
- **Designed for rust and dirt resistance.**
- **Helps emulsify small amounts of water.**
- **Helps provide inherent rust protection.**

Selected specification standards include:

DIN

ISO

Applications

- Marfak Na XD 00 is recommended for use in track rollers of crawler tractors, steering gears, and final drives of tractors where leakage with the normally recommended oil is excessive. It can also be used in industrial gear boxes designed for grease lubrication.
- Marfak Na XD 00 is recommended for chassis lubrication for certain types of passenger cars, trucks, buses, farm, and construction systems when such type of Sodium grease is requested. It is also recommended for centralized lubrication systems.

Warning: be aware of the compatibility with other thickeners.

Approvals, performance and suitable for use

Performance

	DIN 51 502	ISO 6743-09	Operating temperature
Marfak Na XD 00	G 00 H-20	ISO-L-XBBAA 00	-20°C up to +95°C

Product maintenance and handling

Maintaining a clean work environment is critical when equipment greasing is performed. Grease fittings should be wiped clean prior to grease injection to prevent contaminants from entering the equipment. Bearing housings should be maintained one-third to one-half full of grease. Over-greasing should be avoided as excessive heat build-up can result. Periodic relubrication via grease gun or centralized system should be supplemented by complete cleaning and packing with fresh grease on an appropriate schedule.

Typical test data		
Test	Test Methods	Results
Typical Shelf Life: 36 months from date of filling indicated on the product label		
Appearance	Visual	Dark green, smooth, fibrous
NLGI grade	ASTM D217 mod	00
Penetration worked, mm/10	ISO 2137	400 - 430
Thickener type		Sodium
Base oil type		Mineral
Base oil viscosity at 40°C, mm ² /s (base oil mix+polymers)	ASTM D445	1100
Dropping Point, °C	IP 396	NA
Emcor corrosion test distilled water	IP 220	0/0

The typical test data set out above does not constitute a specification. It is indicative only and can be affected by allowable production tolerances. Chevron may modify this test data. Modified data will supersede all previous data, so please ensure you refer to the latest version of this Product Data Sheet (PDS).

Disclaimer: Data provided in this Product Data Sheet (PDS) is based on standard tests under laboratory conditions and is indicative only. This product should not be used for any purpose other than those expressly set out in this PDS. The user has sole responsibility for verifying that this product is suitable for the user's intended application. Neither Chevron nor its subsidiaries (i) make any warranty or representation as to the accuracy or completeness of this PDS; and/or (ii) accept liability for any loss or damage suffered as a result of the use of this product other than in accordance with the terms of this PDS.

When disposing of used product, take care to protect the environment and follow local legislation.

Safety Data Sheets (SDS's) are available for all Chevron products. If you require a SDS or any further information regarding a Chevron product, please contact your local sales office or see www.texacolubricants.com.

A Chevron company product